

**SAUDI ORIGIN HS PETCOKE Ref#2.1  
TYPICAL PROPERTIES**

	<b>Basis</b>	<b>Unit</b>	<b>Test Method</b>	<b>Value</b>	<b>Comment</b>
Moisture		wt. %	ASTM D-7582	Max 12 %	Specification Limit
Ash	Dry Basis	wt. %	ASTM D-7582	Max 4 %	Specification Limit
Volatile Content	Dry Basis	wt. %	ASTM D-7582	Max 12,0 %	Specification Limit
Sulfur	Dry Basis	wt. %	ASTM D-4239	Max 8,0%	Specification Limit
HGI			ASTM D-5003	Min 40	Specification Limit
Gross Calorific Value	Dry Basis	Kcal/kg	ASTM D-5865	8474	Test result
Net Calorific Value	Dry Basis	Kcal/kg	By-Calculation	8308	Test result
<i>Size Distribution + 4.75mm</i>		wt. %	ASTM D - 5709	Min 30 %	Test result
<i>Size Distribution - 4.75mm</i>		wt. %	ASTM D - 5709	Max 70 %	Test result