

**US ORIGIN HS PETCOKE Ref #1.2
TYPICAL PROPERTIES**

Guaranteed moisture: 8%

	Basis	Unit	Test Method	Weekly Composites
Volatile Materials	Dry Basis	%	ASTM D7582	9,94
Ash	Dry Basis	%	ASTM D4422	0,34
Fixed carbon	Dry Basis	%		89,72
Sulfur	Dry Basis	%	ASTM D4239	3,47
HGI			ASTM D5003	83
Gross Calorific Value	Dry Basis	BTU/lb	ASTM D5865	15581
Shot Content		%		5
Vanadium	Dry Basis	ppm	ASTM D6376	434
Nickel (Ni)	Dry Basis	ppm	ASTM D6376	197
Iron (Fe)	Dry Basis	ppm	ASTM D6376	289
Silicon (Si)	Dry Basis	ppm	ASTM D6376	340