

**US ORIGIN HS PETCOKE Ref #1.1  
TYPICAL PROPERTIES**

Guaranteed moisture: 8%

	<b>Basis</b>	<b>Unit</b>	<b>Test Method</b>	<b>Value</b>	<b>Comment</b>
Ash	Dry Basis	wt. %	ASTM D4422	0,25	Anticipated value
Volatile Materials	Dry Basis	wt. %	ASTM D7582	10,5	Anticipated value
Sulfur	Dry Basis	wt. %	ASTM D4239	5,7	Anticipated value
HGI			ASTM D5003	45	Anticipated value
Gross Calorific Value	Dry Basis	BTU/lb	ASTM D5865	15000	Anticipated value
Vanadium	Dry Basis	ppm(wt.)	ASTM D6376	775	Anticipated value
Nickel (Ni)	Dry Basis	ppm(wt.)	ASTM D6376	260	Anticipated value